

GRANSTONE

The only approved coating system for Granwood Floors in non-sport and heavy duty areas



GRANWAX
Products Limited

Description: GRANSTONE is a specially formulated coating system for use on Granwood and timber floors subject to extremely heavy wear.

GRANSTONE offers the following benefits to the user/specifier:-

- Exceptional chemical and abrasion resistance, ideal for use in assembly halls, dining halls, village and community halls, public houses, nightclubs, etc.
- Deep gloss finish
- Free flowing, fast drying and easy to apply
- Offers low maintenance finish, which can be easily cleaned by spot mopping or buffing

Products: **GRANSTONE BP (Binding primer seal)**
GRANSTONE HIGH SOLIDS (High resin build finish)

Preparation: It is important that operatives are conversant with all aspects of procedures prior to commencing work. Please read our information sheet "**Recommended Procedure to Prepare & Recoat Granwood Flooring in General Locations**".

Please note that grit grades in the preparation procedure are offered as a guide only. Operatives must ensure that sufficient "key" is created to enable good adhesion of new coatings.

It is essential to ensure adequate ventilation at all times throughout procedure. The room/floor temperature must be a minimum of 10°C before application.

The surface to be re-coated must be thorough dry, free from dirt, dust and any previous maintenance treatments. Ensure that Granstone is compatible with previous finish before overcoating. If any doubts exist as to compatibility please contact our office, or your local representative, for advice. For full preparation information, please see our relevant data sheet before commencing application.

Application: Apply Granstone evenly using a Granwax Granleda applicator and pad. Heavyweight 'Padco' coaters are recommended for use on larger areas. Take care not to leave pools, runs or drip marks, which will detract from the overall appearance of the floor. Subsequent coats may be applied as soon as the surface is tack-free (approximately 4 – 6 hours, dependant on site conditions). If the floor is to be left overnight before overcoating, it is important that the surface is lightly abraded using a suitable grade of sandpaper or sandscreen disc to ensure good adhesion of the next coat.

For machine sanded Granwood floors, three coats of Granstone are recommended to provide an excellent hardwearing finish.

When overcoating floors, two coats of Granstone are recommended.

Once final coat has been applied, the floor should be left for a minimum of 60 hours prior to light traffic being permitted. The finished floor will continue to harden for a period of 7 days. Cleaning chemicals should be avoided during this period.

Maintenance: For maximum durability and safety it is essential that the correct maintenance schedule is followed. For advice on maintenance, please refer to our "**Maintenance Schedule for Granwood floors in Non-Sporting Areas**", available upon request. Alternatively, arrange a visit by your local Granwax representative by contacting our Head Office on 01773 541177.

Under no circumstances should polish be applied to sports surfaces

Drying Time:	Approximately 4 – 6 hours at 20°C Room Temperature/50% Relative Humidity. Drying times will be entirely dependant upon site conditions.
Coverage:	Approximately 50 - 80m ² per 5 litre. This coverage rate is offered as a guide only as surface porosity will vary considerably.
Pack Size:	5 litre containers
Storage and Handling:	Store in a cool, dry place. Protect from frost. Shelf life: 4 months from date of delivery
Health & Safety:	For health and safety information, please refer to our Material Health & Safety Data Sheet.

The information provided herein is correct to the best of our knowledge. No liability for any errors or opinions is accepted. You should satisfy yourself before applying any of the information contained herein to your particular circumstances. Granwax Products Limited can accept no responsibility for any loss as a result of any person placing reliance on any information contained herein.

Granwax cannot accept any liability for any loss or damage arising from the use of this product if used in areas subjected to severe abrasion, i.e. broken glass or impact damage. Prospective users should therefore satisfy themselves by appropriate trials that the product to be used is suitable for the intended purpose.

Granstone

*This data sheet supersedes any previous issues
September 2015*

**GRANWAX PRODUCTS LIMITED
WEST STREET
RIDDINGS
ALFRETON
DERBYSHIRE DE55 4EW
Telephone: 01773 541177
Fax: 01773 541429
Email: info@granwax.com
Web: www.granwax.com**